



Soudaflex 14LM

Revision: 8/09/2015

Page 1 from 2

Technical data

Basis	Polyurethane
Consistancy	Stable paste
Curing system	Moisture curing
Skin formation	40 to 60 min
Curing speed *	1,5 mm / 24h
Hardness	19 ± 5 Shore A
Density	1,30 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	± 25 %
Temperature resistance	$-30 \ ^{\circ}\text{C} \rightarrow 90 \ ^{\circ}\text{C}$
Max. tension (DIN 53504)	1,50 N/mm ²
Elasticity modulus 100% (DIN 53504)	0,20 N/mm ²
Elongation at break (DIN 53504)	> 800 %
Application temperature	$5 ^{\circ}\text{C} \rightarrow 30 ^{\circ}\text{C}$

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Soudaflex 14LM is a high quality, elastic, 1component sealant based on polyurethane.

Properties

- Very easy to apply
- Permanent elastic after curing
- Very good adhesion on many materials
- Excellent resistance to UV radiation
- Low modulus

Applications

- All usual building joints with high movement.
- Connection joints between window- and doorframes and walls.
- Expansion joints between many different construction materials.
- Joints with large movement.

Packaging

Colour: white, concrete grey, dark gey, light brown, dark brown, dark beige *Packaging*: 310 ml alu cartridge, 300 ml sausage, 600 ml sausage

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between $+5^{\circ}$ C and $+25^{\circ}$ C.

Substrates

Substrates: all usual building substrates, brick, concrete, metals, ... Nature: clean, dry, free of dust and grease.

Surface preparation: Apply Primer 100 on porous substrates. Always use Primer 100 on natural stone, no primer on non-porous substrates. No adhesion on glass. We recommend a preliminary adhesion test on every surface.

Joint dimensions

Min. width for joints: 5 mm *Max. width for joints*: 30 mm *Min. depth for joints*: 5 mm Recommendation sealing jobs: joint width = 2 x joint depth.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Everdongenlaan 18 - 20 Fax: +32 (0)14-42.65.14





Soudaflex 14LM

Revision: 8/09/2015

Page 2 from 2

Application method

Application method: With manual- or pneumatic caulking gun. Cleaning: Clean with white spirit or Surface Cleaner immediately after use. Finishing: With a soapy solution or Soudal Finishing Solution before skinning. Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

 When painted with oxidative drying paints disturbances in the drying of the paint may occur (we recommend to do a compatibility test before application).

Environmental clauses

Leed regulation:

Soudaflex 14LM conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.